



95-R Longer-lasting removability on surfaces from glass to cardboard

95-R introduces the latest adhesive technology for excellent long-term removability with Mastertac paper sheet products. High initial tack on surfaces from glass to cardboard means this one adhesive covers a wide range of removable labelling needs.

Minimal adhesive residue on-press and good die-cutting properties reduce maintenance downtime and support productivity in conversion. And with 95-R's new anti-ageing formulation, you can stock with confidence, reduce waste, and respond to the fastest lead times.

- Excellent initial adhesion and long-term removability
- New anti-aging formulation for increased shelf-life
- New low-odour formulation
- ISEGA approval for direct contact with dry, moist and non-fatty foodstuffs

Face quality (Sales code)		Sales code	Sheet size (cm)	W1 no-score backprint (EAN code)	W3 score backprint (EAN code)	Package size sheets per ream
Vellum M-FSC (CKM)	Old code	CKM 90-R 39	50 x 70	7127279	7127262	250
	New code	CKM 95-R 39	50 x 70	7152066	7152073	250
Machine Coated Plus-FSC (CKN)	Old code	CKN 90-R 39	50 x 70	7127361	7127378	250
	New code	CKN 95-R 39	50 x 70	7152097	7152080	250
Gloss Coated-FSC (CKP)	Old code	CKP 90-R 39	50 x 70		7127521	250
	New code	CKP 95-R 39	50 x 70		7152103	250
High Gloss White-FSC (CKQ)	Old code	CKQ 90-R 39	50 x 70		7127606	250
	New code	CKQ 95-R 39	50 x 70		7152110	250

MASTERTAC TECHNICAL INFORMATION

02/2015 ENG 656

ADHESIVE	95-R
Removable	95-R (sales code)
Type	Removable adhesive for sheets.
Composition	Acrylic, water borne.
Use	A general purpose removable adhesive designed for sheets laminates. Good long-term removability. Good cohesion and adhesion at difficult substrates.

Typical technical values

Tack min	3	N	FTM9
Shear min	6	h	FTM8
Labelling temperature min	5	°C	
Service temperature min	0	°C	
Service temperature max	80	°C	
Limitations	Not recommended for labelling PVC or acrylic coated surfaces, long term removability might be restricted.		
Approvals	The research centre ISEGA has given the adhesive approval for dry, moist and non-fatty foodstuff.		
Shelf life	From the date of manufacture 2 years at +20 deg C and RH 50%. Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.		

Disclaimer

Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. This publication replaces all previous versions. All information is subject to change without notice.