



New Coated Board face

Our new Board 180-FSC (FHR) is an optimal solution for labelling applications requiring high stiffness.

At 180 g/m², this FSC-certified label face is suitable for uses including premium promotional labels, point-of-sale promotional displays and wall decoration labels.

Combination	Sales code (extrapermanent adhesive)	Size (cm)	Packaging (reams)	MOQ	Sheet EAN code
				Wrapped	Solid, unprinted backing (WO)
Board 180-FSC	FHR/98-H/39/WO	50 x 70	125	5000	7161648
		100 x 70	100	2500	7161655

This new product **replaces our Board 170 PEFC (CXJ)** as existing stock runs out, from November 2016 onwards.

- Improved peel-off properties
- FSC-certified from sustainably managed forests
- Higher whiteness
- Higher substance (g/m²)
- Better printing properties

Product comparison	Board (CXJ)	Board 180-FSC (FHR)
Substance (g/m ²)	170	180
Thickness (µm)	210	182
Brightness (%)	90	100

For further information, please contact your UPM Raflatac Area Sales Manager and/or Customer Service.

MASTERTAC TECHNICAL INFORMATION

09/2016 ENG 3901

SELF-ADHESIVE SHEETS

FACE	BOARD 180-FSC
Board	FHR (sales code)
Product	Coated, wood-free, mid-gloss board

Use General board uses where very high stiffness is required like premium promotional labels/stickers, self-adhesive trading cards, wall decoration labels and point-of-sales promotional displays.

Typical technical values

Substance	180	g/m ²	ISO 536
Caliper	182	µm	ISO 534
Brightness	100	%	ISO 2470
Roughness	1.8	µm	ISO 8791-4
Opacity	98	%	ISO 2471
Gloss	35	%	Hunter 75°
Printability	Offset, gravure, flexo, digi printable with xeikon.		
Sustainability	The product named as FSC is registered to SGSCH-COC-004879 FSC™ Mix credit.		

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.